

Wall2Floor Easyflat

Low shrinkage cement level for "Wall2Floor system".

PRODUCT DESCRIPTION Wall2Floor Easyflat is a low shrinkage cement level, made up of selected natural sands, binders and special additives that guarantee perfect adhesion to the substrate and excellent workability.

Wall2Floor Easyflat it can be applied in thicknesses between 3 mm and 20 mm per layer. To obtain thicknesses greater than 3 mm, the surface must be divided into compartments.

APPLICATIONS

Horizontal leveling on non-planar absorbent mineral surfaces, for further information consult the technical data sheet "Wall2Floor system".

IDENTIFICATION CHARACTERISTICS

Nature of the binder: White cement and synthetic resins. Appearance: powder.

PERFORMANCE CHARACTERISTICS Wall2Floor Easyflat allows you to create a compact and uniform surface.

SUPPORT PREPARATION

See technical data sheet of "Wall2Floor system".

APPLICATION

See technical data sheet of "Wall2Floor system".

DILUTION

Use 4 l of clean water for each 25 kg bag of product. Mix the product with a mechanical mixer equipped with a whisk for about three minutes, the mixture obtained must not have lumps, unmixed portions of the components, impurities. Pot life of mix: approximately 20 minutes at 25 ° C, RH = 60%. Drying time varies greatly depending on the thickness applied and the environmental conditions. Up to 3 mm of thickness applied about 6-8 hours; over 3 mm thickness applied up to 3 days.

RECOMMENDATIONS

During all phases of preparation of the substrate, products and application, the correct use of equipment and personal protective equipment (dpi) is recommended.

Do not expose the products for long periods to direct heat sources or temperatures below + 5 ° C.

If the products are stored at temperatures close to + 5 ° C, we recommend that you take them to a suitable temperature before use, in order to condition them at a temperature of use not lower than + 10 ° C. Do not heat the products using a direct source of heat, flame, hot body or similar. We recommend that you finish each job with materials from the same manufacturing batch. In the case of use of different manufactures it is advisable to mix the various productions together. For the correct use of the mentioned materials, dilution and installation, please refer to a careful reading of the relative technical data sheet.

During all phases of preparation of the substrate, products and application, the correct use of equipment and personal protective equipment (dpi) is recommended.

CLEANING OF TOOLS

With water immediately after use.

SURRENDER

Wall2Floor Easyflat (referring to dust): 2.5 - 6.8 kg / m², per layer, for thicknesses of 5 mm. It is advisable to check the actual yield with a preliminary test on the specific support.

COLOR

Not tinted.

PACKING

25 kg bags.

STORAGE TERMS

The material has a shelf life in the original and well sealed container of about 12 months as long as it is stored in a covered warehouse at a temperature between + 10 ° C and + 30 ° C.

Contains: cement

H318 Causes serious eye damage. H315 Causes skin irritation. H335 May cause respiratory irritation. H317 May cause an allergic skin reaction. P101 If a doctor is consulted, keep the container or product label available. P102 Keep out of the reach of children. P501 Dispose of contents / container in accordance with national regulations.

For further information consult the safety data sheet.

NB- COLORIFICIO NOVACOLOR guarantees that the information in this sheet is provided to the best of its experience and its technical and scientific knowledge; however, it cannot assume any responsibility for the results obtained with their use as the conditions of application are beyond its control. It is advisable to always check the actual suitability of the product for each specific case. This cancels and replaces any previous card.